

TRANSCOL LADRIFAST ADHESIVE WHITE

Fast-setting cementitious base construction glue

COLOUR
White

PACKING
25kg bag

USE
Exterior/ Interior

THEORETICAL CONSUMPTION
Single: 3 to 4 g/m²/mm
Double: 4 to 5 kg/m²/mm

1. PURPOSE

Construction glue, type C2F, suitable for gluing pieces on pieces, of various materials, such as:

- ◆ tiles and cement tiles;
- ◆ stone materials (as long as they are resistant to humidity and not subject to efflorescence);
- ◆ ceramic tiles of all types of medium and large format.

2. TECHNICAL DATA

Property	Value
Volumic mass (powder)	1400 ± 200 Kg /m ³
Open time	10 min ≥ 0.5 N/mm ²
Initial adhesion	≥ 1 N/mm ²
Adhesion after immersion in water	≥ 1 N/mm ²
Adhesion after heat action	≥ 1 N/mm ²
Adhesion after freeze-thaw cycles	≥ 1 N/mm ²
Reaction to Fire	Class E

Results obtained according to EN 12004-1 under controlled conditions

3. COMPOSITION

Washed siliceous sand, white cement, calcium carbonate, inorganic additives and adjuvants, water-retaining additives and synthetic fibers.

4. SUPPORT

The cement-based supports are plaster, screeds and concrete. An adhesion promoter must be applied to reinforced concrete surfaces.

Concrete or masonry supports, wall or floor must be more than 30 days old. Plaster and subfloor mortar with batten or unplanned must be more than 14 days old.

The substrate and the parts to be applied must be clean, free of dust, paint residues, grease and formwork oils.

If the glue is carried out on vertical supports with high absorption, they must be moistened before applying the adhesive cement.

It should be applied to the flat and regular wall, with a surface warping of no more than 2 mm per linear meter, proceeding, if necessary, to its correction.

Do not apply:

- ◆ in barbecues, fireplaces, swimming pools;
- ◆ on substrates with humidity greater than 4%;
- ◆ on zero-absorption supports.

5. PREPARATION

Mix the contents of the 25Kg bag with approximately 3.75 litres of clean water until you get a homogeneous dough, without lumps.

Mixing is preferably carried out mechanically with a low-speed mechanical agitator.

Once mixed, the mortar should be used immediately.

6. APPLICATION

Spread the glue well with a comb or notched trowel (8 to 10 mm). The mortar removed by the teeth of the trowel must be remixed with the rest.

Then place the piece to glue by tightening it with vibratory movements. Hit lightly with a rubber hammer, without damaging the surface of the ceramic pieces.

Provide joints of at least 2 mm between the pieces, which must be filled with mortar and a joint capable of absorbing the dimensional variations of the pieces. Joint putty can be applied between 24 to 48 hours after gluing.

Whenever greater efficiency or gluing of larger parts is desired, a double glue should be made. This type of bonding is applied to parts with an area greater than 625 cm² and in areas of heavy traffic.

Once applied, it has a setting time of 20 minutes.

Clean all excess mortar immediately after laying the ceramic tiles, with a slightly damp sponge, only with clean water.

The floor can be used by the construction personnel with care after 4 hours.

7. SAFETY

It is recommended to use a dust mask to protect the respirable crystalline silica, goggles and gloves when handling the product. If there is contact with eyes, rinse thoroughly with clean water. Do not ingest. Refer to the Product Safety Data Sheet.

8. USEFUL ADVICE

- ◆ Application temperature from 5°C to 30°C;
- ◆ Excess water in the preparation alters the physical characteristics of the product;
- ◆ Never add any other type of product to the mortar;
- ◆ Never use acid or excess water to clean mortar residues;
- ◆ Do not apply in rain, very humid environment or strong wind;
- ◆ Do not apply on icy surfaces or those at risk of frost within 24 hours of applying the product.

9. STORAGE

Store in a dry and ventilated place, on the pallet and in the original closed and protected packages, for 180 days from the date of manufacture.